



## Epilux 4 Zinc Rich Primer Z-88

### USES

Suitable for application as a priming coat on structural steel, pipelines, tank exteriors, etc., of refineries, petrochemicals, fertilizers, power generation plants, mining facilities and bulk handling equipment.

### SCOPE

A high performance epoxy primer heavily loaded with metallic zinc. It imparts excellent cathodic protection when applied over blast cleaned steel. It has been specially designed for application on structurals, tank exteriors which are exposed to highly saline and/or corrosive environments.

#### PRODUCT DATA

**Type :** Two Pack, cured with Polyamide

**Composition :** Epoxy resin/metallic zinc

**Mixing Ratio :** Base : Catalyst – 3 : 1 by volume

**Pot Life :** 6–8 hours

**Application :** Brush, Conventional or Airless Spray

**Recommended DFT :** 35–50 microns per coat

**Corresponding WFT :** 78–111 microns per coat

**Theoretical Spreading Rate :** 9.0–12.8 Sq. Mtr./Ltr.

**Drying Time :**

TOUCH : 15–30 minutes  
HANDLE : 2–3 hours  
HARD : 4–6 hours

**Curing Time :** 7 days

**Overcoating Interval :**

MIN : Overnight  
MAX : Indefinite

**Flash Point :** Above 22° C

**Colour :** Grey

**Finish :** Matt

**Packing :** 20 Ltrs.

**Thinner/Cleaner :** Thinner 844

**Storage Life :** Upto six months as long as the sealed containers are kept under cover in a dry place under normal temperature conditions.

#### RESISTANCE GUIDE

**Chemical Resistance :**

| EXPOSURES | SPLASH & SPILLAGE | MILD FUMES / OUTDOOR RESISTANCE |
|-----------|-------------------|---------------------------------|
| Acids     | Fair              | Very Good                       |
| Alkalis   | Fair              | Very Good                       |
| Solvents  | Excellent         | Excellent                       |
| Salt      | Excellent         | Excellent                       |
| Water     | Excellent         | Excellent                       |

**Note :** In chemical environments, adequate performance is obtained with a suitable top coat

**Temperature Resistance :**

Continuous : 200° C  
Intermittent : 300° C

**Weatherability :** Excellent. Should be top coated for maximum durability.

**Flexibility :** Good

**Abrasion Resistance :** Very Good

**SURFACE PREPARATION**

Remove grease, oil and other contaminants preferably by using Bison Degreasing Solvent. Blast clean to a minimum of Sa 2 1/2, Swedish Standard SIS 05 5900. For severe corrosive conditions blast to Sa 3 with a surface profile not exceeding 35–40 microns.

Special care must be taken on weld areas to remove flux and spatter. Welds should be ground back to avoid pockets where corrosion can occur. The cleaned surface should be coated before it becomes contaminated.

**APPLICATION**

Stir the base thoroughly and then mix three parts base and one part catalyst by volume to uniform consistency.

**Brush** : Apply without thinning.

**Conventional Spray** : Normally no thinning is required. However, addition of Thinner 844 upto 5% is recommended for ease of application. Use any standard equipment at an atomising pressure of 3.5–4.2 Kg/cm<sup>2</sup>.

**Airless Spray** : Apply without thinning. Use any standard equipment having pump ratio 30 : 1. Tip size 0.38–0.48 mm. Tip pressure 110–160 Kg/cm<sup>2</sup>.

**TYPICAL PAINTING SPECIFICATIONS**

| Surface | 1st Coat                 | 2nd Coat                          | 3rd Coat                          | 4th Coat                 |
|---------|--------------------------|-----------------------------------|-----------------------------------|--------------------------|
| Steel   | Epilux 4 Z/R Primer Z-88 | Epilux 4 HB MIO                   | Epilux 4 HB Epoxy Finish          | Epilux 4 HB Epoxy Finish |
| -do-    | -do-                     | Epilux 155 HB or Epilux 89 HB     | Epilux 155 HB or Epilux 89 HB     |                          |
| -do-    | -do-                     | Epoxy PU HB or Bergerthane        | Epoxy PU HB or Bergerthane        |                          |
| -do-    | -do-                     | Epilux 5 CTE or Epilux 555 CTE HB | Epilux 5 CTE or Epilux 555 CTE HB |                          |
| -do-    | -do-                     | Linisol HB MIO                    | Linisol C/R Paint                 | Linisol C/R Paint        |

**Notes :**

1. Use off the mixed paint within the stipulated pot life period.
2. Do not apply when temperature falls below 10° C or rises above 50° C and when relative humidity rises above 90%. Do not apply during rain, fog or mist.
3. Brushes and spray equipment should be cleaned with Thinner 844 otherwise equipment is likely to be damaged.
4. Priming with Epilux 4 Zinc Rich Primer Z-88 is also known as "cold galvanising".

**Health & Safety** : Please refer to the separate Safety Data Sheet available with detailed information.

**DISCLAIMER**

The information contained within this Data Sheet is based on information believed to be reliable at the time of its preparation. The Company will not be liable for loss or damage howsoever caused including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

**DATA SHEET No. : 037**  
**Issue Date : Mar. 04**

**BERGER PAINTS INDIA LIMITED**

Berger House, 129 Park Street, Kolkata 700017 **Phone** : (033) 2229 9724 (5 lines) / 249 9754 (4 lines) **Fax** : 91-33-2249 9729 / 2249 9009  
**Email** : **NORTH** : bpil\_okh@mantraonline.com **SOUTH** : bpil\_ch2@sify.com **EAST** : bpil\_cl1@vsnl.net **WEST** : bpil\_vsh@vsnl.net